

Received: 10/24/2007	Completed: 10/31/2007	Letter: Z2	rb	P.O.#: 0000038043	Test Report #: 2-70476-2-
Client's Identification	Blackout Satin. 58" Wide. 100% Polyester. Used For Stage and Display Draperies.				
Tested For: Bob Bertrand, Gen. Mgr.			Key Test: CA 1237 Sm		105
Rose Brand 4 Emerson Lane Secaucus, NJ 07094			Tel: 1-(800)-223-1624 Fax: 1-(201)-809-1851		Ext: 115

PC: 1H /jd

TEST PERFORMED: California Fire Marshal Title 19: Section 1237 (Proposed Revision 8/9/93) Fire Resistance; Small Scale Test - INTERIOR MATERIALS QUALIFICATION

RESULTS REPORTED: ☒ Initially
☐ After 3 dry cleanings
☐ After 5 launderings @ 160°F

RESULTS:	Specimen #	Afterflame (seconds)	Afterglow (seconds)	Char Length (inches)
Warp:	1	0.0	0.0	4.4
	2	0.0	0.0	1.1
	3	0.0	0.0	3.5
	4	0.0	0.0	2.4
	5	2.0	0.0	3.4
	Avg:	0.4		
Fill:	6	14.0	0.0	4.3
	7	5.0	0.0	3.1
	8	0.0	0.0	3.0
	9	0.0	0.0	4.1
	10	0.0	0.0	3.3
	Avg:	3.8		

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 7.7 oz/yd²

ACCEPTANCE CRITERIA:

Afterflame: 4.0 seconds maximum average for warp or fill
Afterglow: (see Note #2 below)
Char Length: 6.0 inches maximum for any individual specimen

Notes:

1. An asterisk (*) next to any char length measurement indicates that a part of the char length is melt away due to heat from the flame source and not from propagating flame. Therefore, the sample submitted meets the requirements of Title 19 - California Code of Regulations, Section 1237 and 1237.1 for materials weighing less than 4 oz/yd².
2. Afterglow is required to be reported; however, it is not factored into the Acceptance Criteria.



The
Govmark
Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Page 2

Received: 10/24/2007	Completed: 10/31/2007	Letter: Z2	rb	P.O.#: 0000038043	Test Report #:	2-70476-2-
Client's Identification	Blackout Satin. 58" Wide. 100% Polyester. Used For Stage and Display Draperies.					
Tested For: Bob Bertrand, Gen. Mgr. Rose Brand 4 Emerson Lane Secaucus, NJ 07094				Key Test: CA 1237 Sm		105
				Tel: 1-(800)-223-1624		Ext: 115
				Fax: 1-(201)-809-1851		

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:


☒ Complies; ☐ Does not comply

REMARKS: None.

NOTE: In August 1993 the State Fire Marshal issued a proposed revision, which permitted a maximum average Afterflame of 4.0 seconds. This proposed revision was honored by the subsequent State Fire Marshals until approximately February 2004, at which time the State Fire Marshal's office reverted to the unrevised rule of 1 second maximum average for interior fabric.

In a conversation with the latest California State Fire Marshal on August 9, 2007, it was learned that the proposed 1993 revision is now back in effect. In addition to allowing 4 seconds Afterflame rather than 1 second, the proposed revision provides for testing of 10 specimens, rather than 6 specimens.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by California Fire Marshal Title 19: Section 1237 Small Scale (Proposed Revision 8/9/93).



AUTHORIZED SIGNATURE

THE GOVMARK ORGANIZATION, INC. /jb

MS. HEATHER ROBERTSON

(Page 2 of 2)