



The
Govmark
Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Page 1

Received: 10/24/2007	Completed: 10/31/2007	Letter: Z	rb	P.O.#: 0000038043	Test Report #: 2-70476-0-
Client's Identification	Blackout Satin. 58" Wide. 100% Polyester. Used For Stage and Display Draperies.				
Tested For: Bob Bertrand, Gen. Mgr.		Key Test: NFPA 701-89 Sm			105
Rose Brand		Tel: 1-(800)-223-1624			Ext: 115
4 Emerson Lane		Fax: 1-(201)-809-1851			
Secaucus, NJ 07094					

PC: 1H

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Resistant Textiles and Films 1989 Edition (Small Scale Procedure for Curtains & Draperies Weighing Less than 10 oz/yd²)

Note: NFPA 701 - 1989 Edition was specified by the older building codes for draperies, window treatments, and similar hanging decorations. The older building codes required both the Small Scale and Large Scale Tests.

In 1996 NFPA 701 was revised and an entirely different test was developed for draperies, window treatments, and similar hanging decorations. This single test (which replaces the 1989 Tests) is designated as Test Method 1.

RESULTS REPORTED: ☒ Initially
☐ After 3 dry cleanings
☐ After 5 launderings @ 160°F

RESULTS:	Specimen #	Afterflame* (seconds)	Flaming Drip (seconds)	Char Length (inches)
Length:	1	5.0	0.0	3.5
	2	20.0	0.0	5.0
	3	0.0	0.0	4.4
	4	12.0	0.0	5.2
	5	0.0	0.0	4.0
Width:	6	0.0	0.0	3.8
	7	13.0	0.0	4.7
	8	0.0	0.0	4.8
	9	0.0	0.0	2.7
	10	0.0	0.0	4.8
		Avg: 0.0	Avg: 4.3	

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 7.7 oz/yd²

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

☒ Complies; ☐ Does not comply; ☐ Requires testing of 5 additional specimens



The
Govmark
Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Page 2

Received: 10/24/2007	Completed: 10/31/2007	Letter: Z	rb	P.O.#: 0000038043	Test Report #: 2-70476-0-
Client's Identification	Blackout Satin. 58" Wide. 100% Polyester. Used For Stage and Display Draperies.				
Tested For: Bob Bertrand, Gen. Mgr.			Key Test: NFPA 701-89 Sm		105
Rose Brand 4 Emerson Lane Secaucus, NJ 07094			Tel: 1-(800)-223-1624 Fax: 1-(201)-809-1851		Ext: 115

ACCEPTANCE CRITERIA:

Afterflame (seconds)	Flaming Drip (seconds) Maximum Average	Char Length (inches)	
		Max.Avg.	Max.Ind.Spec.
*	2.0	6.5"	7.5"

* Afterflame is required to be recorded;
however, it is not factored into the Acceptance Criteria.

RETEST PROVISION:

Test 5 additional specimens if only 1 specimen exceeds 7.5" Char Length.

REMARKS: None.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 1989 Edition Small Scale Procedure for Curtains and Draperies.

Heather E. Robertson

AUTHORIZED SIGNATURE
THE GOVMARK ORGANIZATION, INC. /jb

MS. HEATHER ROBERTSON

(Page 2 of 2)