



ROSE BRAND

32 oz. Imperial Velour, IFR

FABRIC SPECIFICATIONS

| | | | |
|-------------------------|--------------------|---------------------------|---------------------|
| Weight/Linear Yard | 32 oz./lin yard | Pattern Number | 640 |
| Pile Yarn & Count | 29/2 100% IFR Poly | Ground Yarn & Count | 2/150/96 IFR Poly |
| Pile Weight | 1.306 lbs/lin yard | Ground Weight | .3406 lbs/Lin. Yard |
| Pile Weight/ % of Total | 65% | Ground Weight/ % of Total | 35% |
| Pile Ends/Inch. | 51 | Ground Ends/Inch. | 48 |
| Pile Tufts/Sq. Inch. | 1148 | Filling Yarn & Count | 29/2 100% IFR Poly |
| Pile Height/1000" | 136 | Filling Weight | .3563 lbs/Lin. Yard |
| | | Filling Picks/Inch | 47 |

IFR-Inherently Flame Retardant Polyester

PERFORMANCE

This Fabric Meets or Exceeds The Listed Standard Requirements

| <u>Test</u> | <u>Standard Requirements</u> | <u>Test Method</u> |
|---------------------------------------|--|-------------------------------------|
| Abrasion (Heavy Duty) | 50,000 double rubs ANSI/ASTM-D-3597-77 | ASTM-D-1175-71-24 Wyzenbeek Test |
| Tensil Strength: Warp: Filling: | 50 Lbs. Min. 50 Lbs. Min. ANSI/ASTM-D-3597-77 | ASTM-D-1682 |
| Tear Strength: | 6 Lbs. Min. 6 Lbs. Min. ANSI/ASTM-D-3597-77 | ASTM-D-2262 |
| Crocking: | Class 4 Dry Min. Class 3 Med. Min. ANSI/ASTM-D-3597-77 | AATCC-8-1974 |
| Light Fastness: | Fading 60 Hours | AATCC-16A-1974 |

FLAMMABILITY

Manufactured To Meet The Following Requirements

NFPA 701
MVS 302
BIFMA F-1-1978
SC-191-53 Class1 California
UFAC Class 1
NFPA 701



ROSE BRAND NY (800) 923 - 1624 CA (800) 360 - 5056

www.rosebrand.com