



ROSE BRAND

Poly Pro Fabric Specifications

Construction:	Warp Knit
Width:	62.0"+/-1"
Weight (oz./square yd):	8.0 +/- 0.50
Weight (oz./lin yd):	13.75 +/- 0.75
Courses:	66.0 +/- 2
Wales:	34.0 +/- 2
Fiber Blend:	100% Polyester
Martindale Abrasion	
-1600 Cycles Wet	Moderate Minimum
-3200 Cycles Dry	Moderate Minimum
Air Permeability (CFM)	250
Seam Slippage(lbs) Warp	45
	Fill: 40
Trap Tear (lbs) Warp:	13
	Fill: 16
Crocking -- Wet	3.5 minimum
-- Dry	3.5 minimum
Wyzenbeek Abrasion	Exceeds 100,000 d. rubs
Flame Resistance	Tested in accordance with the 1999 NFPA 701 test # 1
ASTM Methods Used	

